



ChemMasters

SPECIALTY CONSTRUCTION PRODUCTS

CRYSTAL CLEAR

HIGHEST GLOSS
SEALER & CURING COMPOUND
FOR CONCRETE

P R O D U C T D A T A

DESCRIPTION

Crystal Clear is premium quality, super high gloss, non yellowing, curing and sealing compound. Crystal Clear is a state-of-the-art proprietary formulation which creates the highest gloss possible on concrete. Crystal Clear coats concrete with a chemically bonded siliconized acrylic film that deepens the color and enhances the look of pigmented or decorative concrete. Crystal Clear completely resists discoloration from ultraviolet light exposure. It is extremely abrasion resistant and keeps its high gloss finish much longer than standard concrete sealers. Crystal Clear will retard efflorescence while resisting oil, grease and food stains. Crystal Clear eliminates concrete dusting, while protecting concrete against salt and water penetration.

USES

Use on exterior plain, colored, textured or exposed aggregate concrete to

- Cure freshly poured concrete where superior curing efficiency is required
- Seal, harden and dustproof existing concrete, particularly architectural or residential concrete exposed to freeze-thaw or Ultra Violet light.
- Enhance the color and and gloss of pigmented or stamped concrete

ADVANTAGES

- Crystal Clear is much tougher than acrylic sealers. The high gloss created by Crystal Clear lasts up to 70% longer.
- Crystal Clear completely resists discoloration from ultraviolet light exposure.
- Crystal Clear cures concrete to ASTM C1315 standards to minimize cracking and increase the strength of concrete.

- Protects surfaces against deicing chemicals, fertilizers, salts, grease, oil, alkalies, mild acids and detergents.

TECHNICAL DATA

Crystal Clear has been tested for gloss retention and non yellowing against standard concrete sealers with the following results.

Gloss Retention

After 1,000 hours QUV exposure
(All panels begin with 95 gloss rating)

	Gloss	Percent Original
Crystal Clear	89.8	95%
Moisture Cure Urethane	79.1	83%
Pure Acrylic	73.6	77%
Styrene Acrylic	55.4	58%

Yellowing Index

After 1,000 hours QUV exposure
Equivalent to approx 10 years of Florida sunlight
(All panels begin with 0 yellow rating)

	Yellowing
Crystal Clear	0.00
Moisture Cure Urethane	3.00
Pure Acrylic	4.77
Styrene Acrylic	9.48

(Visable yellowing begins at 3.00)

- ASTM C-1315, Type I , Class A & B,
- ASTM C-309, Type I, Class A & B,
- AASHTO M-148, Type 1 & 1D, Class A & B
- USDA approved, when cured, for incidental contact

V.O.C. content 685 gm/L



ChemMasters

An American Owned & Operated Company
300 EDWARDS STREET • MADISON, OHIO 44057-3112
(440) 428-2105 • FAX (440) 428-7091 • ORDER LINE: (800) 486-7866
www.chemmasters.net

Revised Sept2003

Moisture retention (ASTM C-156)	0.035 gms/cm ²
Flash point	over 105°F (40.6°C)
Drying time@70°F (21°C) and 50% RH	
Dust free	45 minutes
Hard film	2 hours
Light foot traffic	8 hours
Maximum hardness	7 days

PACKAGING

Crystal Clear is available in 5 U.S. gallon (18.9 liter) metal pails and 55 U.S. gallon (208 liter) drums.

ESTIMATING GUIDE

Coverage is dependent upon surface texture and porosity. These are guidelines only

	Ft. ² /gal	M ² /L
Curing	300	7
Sealing Concrete		
First Coat	350	8
Second coat	450	11

DIRECTIONS

MIXING: Do not dilute. Crystal Clear is packaged ready to use and requires no mixing.

APPLICATION: Always test application in a small area to verify appearance. In cold temperatures (below 50°F), warm material to room temperature to ease application. In hot weather avoid applying in direct sunlight or in windy conditions. In hot weather, apply Crystal Clear early in the morning.

Apply using a short nap roller or brushes. Spray equipment may be used by experienced applicators who know how to apply sealers evenly with sprayers. If spraying, use a low pressure sprayer equipped with a fan nozzle and a .030-.040 orifice tip. Hold sprayer tip 6-8 inches (15-20 cm) from the surface of the concrete. Apply uniformly leaving no pinholes or gaps.

CURING: Apply Crystal Clear after all bleed water has dissipated and application will not mar the surface. For maximum gloss and protection, apply a second sealer coat after curing process is completed (minimum 28 days later).

SEALING: After concrete has fully cured, clean thoroughly with detergent and high pressure water removing any dirt, dust, paints, oil, grease or other

contaminants that prevent adhesion. Allow the surface to dry before application of Crystal Clear. For best protection and highest gloss, apply two thin coats of Crystal Clear. Allow first coat to dry tack free before application of second coat.

MAINTENANCE: Inspect sealed surfaces annually for signs of wear. Clean surface and reapply as necessary.

CLEANUP

Clean tools immediately after use with Polyseal Solvent™ or xylene.

STORAGE

Store tightly sealed containers in cool, dry area away from direct sunlight and sources of heat. Shelf life is one year from date of manufacture.

LIMITATIONS

- Crystal Clear should not be used on surfaces to receive concrete overlays or toppings. Consult ChemMasters for compatibility of other surface treatments. Always test for compatibility and adhesion.
- Strong organic solvents, xylene, toluene, lacquer thinner, will lift Crystal Clear. Gasoline, hydraulic fluids, peanut oil and cooking oils soften and lift Crystal Clear if spills are not removed quickly.
- Do not apply to joints or channels scheduled to receive elastomeric caulks.
- Do not use if ambient or surface temperature is below 40°F (4°C). For best results, condition material to a minimum of 50°F (10°C) prior to application.
- Quality curing or sealing compounds and floor treatments darken or highlight the subtle color variations naturally present in concrete. When the difference in shading caused by absorptive deviation or finishing techniques is objectionable, consult ChemMasters technical staff prior to concrete placement for recommendations.

CAUTION

COMBUSTIBLE LIQUID: Keep away from heat or open flames. Use with adequate ventilation. May cause skin, eye and respiratory tract irritation. Do not take internally.

This Product is Formulated and Labeled for Industrial and Commercial Use Only

FOR BEST RESULTS AND SAFEST USAGE, USER IS SPECIFICALLY DIRECTED TO CONSULT THE CURRENT MATERIAL SAFETY DATA SHEET AND PACKAGE LABEL FOR THIS PRODUCT

We warrant our products to meet our published specifications and to be free from defects in materials and workmanship to the acceptable quality levels defined in these specifications. If acceptable quality levels are not specified, the acceptable quality levels will be those normally supplied by us for the product. We make no guarantee of the results to be obtained from the use of our products. The determination as to the adaptability of any of our products to the specific needs of the Buyer is solely Buyer's prerogative and responsibility. We are glad to offer suggestions on the use of our products. Nevertheless, there are no warranties given except such expresses warranties offered in connection with the sale of a particular product. Our liability shall be limited to replacement of, or refund of an amount not to exceed the purchase price attributed to, the goods as to which such claim is made. Our selection of one of these alternatives shall be Buyer's exclusive remedy. IN NO CASE SHALL WE BE LIABLE FOR CONSEQUENTIAL OR SPECIAL DAMAGES, EVEN IF WE HAVE BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES. THE FOREGOING WARRANTIES ARE IN LIEU OF ALL OTHER WARRANTIES, GUARANTEES, CO-CONDITIONS AND REPRESENTATIONS, EITHER EXPRESSED OR IMPLIED, WHETHER ARISING UNDER ANY STATUTE, COMMON LAW, USAGE OR TRADE, COURSE OF DEALING OR OTHERWISE, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.