



ChemMasters®

Duraguard™ 310CRU

Chemical Resistant Urethane
For Bridge and Wall Coatings

SPECIALTY CONSTRUCTION PRODUCTS

P R O D U C T D A T A

DESCRIPTION

Duraguard 310CRU is a two component, aliphatic polyurethane coating. It may be used as a topcoat over epoxy and epoxy Novolac systems to improve chemical and ultraviolet light resistance.

USES

- Concrete topcoat for D.O.T. applications including Municipal-Bridge Parapets, Bridge Columns, Precast Spans, Bridge Substructure & Superstructure.
- Coatings and toppings requiring ultraviolet light protection

ADVANTAGES

- Optimum chemical resistant coating for use inside or out
- Passes NCHRP 244 testing to protect concrete from chloride ion penetration when used in conjunction with **Safe-Cure & Seal EPX**
- Excellent abrasion resistance when used as a top coat for high build, trowel applied or self-leveling toppings
- Superior resistance to staining and deterioration caused by foodstuffs, acids, alkalis, hydrocarbons
- Exceptional color retention and stability with high gloss finish

Packaging

Package	Part Number
Duraguard 310CRU Part A Resin 5 gal	F5200.00A
Duraguard 310CRU Part B Hardener 1 gal	F5200.00B

TECHNICAL DATA

- ASTM Type V, aliphatic polyurethane coating
- ACI 302, Table 1.1 Class 1, 2, 3, 4, and 5 floors
- Ohio and New York State D.O.T. preapproved as topcoat for epoxy/urethane system for bridges and barrier walls
- Complies with 40 CFR Part 59 <350 g/L V.O.C. for Architectural Coatings

Estimated Coverage Rates

3 to 4 mils dry	200 to 300 ft ² /gal (5 to 7 m ² /L)*
* Use recommended DOT rates where applicable	

Physical Properties

Volatile Organic Compound	<350 g/L
Solids - pigmented Solids - clear	66 to 72% 60%
ASTM B117-73 Salt Resistance	No effect
ASTM D3363 (Pencil Hardness)	> 2 H
Solvent Resistance (100 double rubs)	No effect
Abrasion Resistance-Taber 1000g/1000 cycles CS-17 wheels	25 grams
Gel Time 0.5 cups (150 ml)	90 min
Drying Times:	Hours
Tack Free	5
Moderate Foot Traffic	12 to 24
General Traffic	48
Heavy Wheel Traffic	7 days

Chemical Resistance

Material	Rating
Ammonium Hydroxide	R
Sodium Hydroxide	R
Sodium Chloride	R
Calcium Chloride	R
Tri-sodium Phosphate	R
Ethyl Alcohol	R
Isopropyl Alcohol	R
Methyl Alcohol	R
Auto Brake Fluid	C
Hyjet #3 Brake Fluid	R
Skydrol 500 A & B Brake Fluid	R
Chromic 10% Acid	R
Hydrochloric Acid 31%	R

Continued on page 2



ChemMasters®

An American Owned & Operated Company

300 EDWARDS STREET • MADISON, OHIO 44057-3112 (440) 428-2105 • FAX (440) 428-7091 • ORDERLINE: (800) 486-7866 www.chemmasters.net

March 2019

Chemical Resistance

Material	Rating
Nitric Acid 70%	N/R
Phosphoric Acid 35% & 80%	R, R
Sulfuric Acid 30% & > 50%	R, C
Acetic Acid 5% & 20%	R,R
Glacial Acetic Acid	C
Gasoline	R
Jet Fuel A-1	R
Toluene	R
Methylene Chloride	C
Trichloroethylene	C
Perchloroethylene	C
Butyl Cellosolve	R
Acetone	C
MEK	R
PM Acetate	R
Beer	R
Cola	R
Milk	R
Mustard	R
Bleach	R
Ratings: R= recommended; N/R = Not Recommended; C = Consult ChemMasters	

DIRECTIONS

Duraguard 310CRU may be used as a top coat for all epoxy high build, trowel down, or self-leveling toppings. Apply **Duraguard 310CRU** to primed concrete surfaces only. Use **Safe-Cure & Seal EPX, Duraguard 100WB, or Duraguard 100** as a primer.

Surface preparation is important; follow the recommendations for the selected primer. If the recoat window is missed, for the chosen primer, or the urethane is being applied over an older coating the basecoat must be sanded or screened then swept and solvent wiped prior to urethane application. Contact ChemMasters for additional details.

Coverage Rate: 200 to 300 ft²/gal (5 to 7 m²/L) yields 5 to 8 wet mils and dries to 3 to 4 mils. **When doing DOT work those individual requirements take precedence over any other coverage rates.**

Mixing: Stir or mix **Duraguard 310 CRU Part A, Resin** to disperse pigments, then add the entire contents of 1 gallon of **Duraguard 310CRU Part B Hardener** to the 5 gallon pail of **Duraguard 310CRU Part A**.

Mix at low speed using a drill fitted with a mixing blade for 3 minutes. Pigmented materials must be mixed until color is uniform with no streaks. Apply material within 60 minutes. Working time is drastically reduced when kept in large quantities.

Horizontal and Vertical applications: pour small quantities of the mixed **Duraguard 310CRU** onto horizontal primed area. Spread material evenly using a short nap solvent resistant roller.

Duraguard 310CRU may also be applied with solvent resistant brushes & rollers or sprayed using a GRACO (Gmax 5900 HD) sprayer rated at minimum 1 GPM or comparable airless sprayer combined with a minimum 0.025 GHD fan tip, depending on desired output rate. If using a sprayer flush hoses with solvent prior to spraying **Duraguard 310CRU**.

Recoat: Between 6 and 24 hours depending on the surface temperatures and humidity. If recoating is delayed longer than 24 hours after the material is tack free lightly sand or screen the surface prior to recoating.

Clean Up: Clean tools and equipment immediately after use with xylene (xylol) or PM acetate.

LIMITATIONS

Do not apply when:

- the surface or air temperature is or is expected to be below 50° F (10°C) within 6 hours of application.
 - temperature at the time of application is within 5°F(2.7°C) of the dew point
 - dew, fog, or high humidity is expected within 4 hours of application.
 - rain is expected within 24 hours of application
 - if surface is frozen or frost filled
- Not recommended for waterproofing or damp proofing of exterior horizontal surfaces, floors, or below grade interior walls.
 - Do not apply in areas of immersion or where a negative head pressure may exist.
 - Application in direct sunlight or during times of extreme heat may cause wrinkling, pinholes, or blistering.
 - Schedule application for early morning or late afternoon when ambient and substrate temperatures are at their lowest.
 - Do not use strong caustic or solvent based cleaner. For additional data on good coating practice consult SSPC, NACE, or ICRI.
 - Not recommended for waterproofing or damp proofing of exterior horizontal surfaces, floors or below grade interior walls. Iron particles in block, brick or mortar may cause discoloration through the coating. Keep from freezing.

STORAGE: Store unmixed factory sealed containers in cool dry place out of direct sunlight. Shelf life of properly stored material is 2 years from the date of manufacture.

PRECAUTIONS.

Part A Warning: Flammable Liquid and Vapor. Harmful if swallowed. Causes eye irritation. Causes skin irritation. Harmful if inhaled. May cause respiratory irritation. May cause drowsiness or dizziness. May cause damage to kidneys, liver, brain and nervous system through prolonged and repeated exposure by inhalation.

Part B: Danger: Flammable Liquid and Vapor. Causes serious eye irritation. May cause allergic skin reaction. May cause allergy or asthma symptoms or breathing difficulties if inhaled.

Consult Safety Data Sheet for complete hazard information.

For professional use only
Keep out of reach of children

This Product is Formulated and Labeled for Industrial and Commercial Use Only

FOR BEST RESULTS AND SAFEST USAGE, USER IS SPECIFICALLY DIRECTED TO CONSULT THE CURRENT PRODUCT & SAFETY DATA SHEETS AND PACKAGE LABEL FOR THIS PRODUCT. We warrant our products to meet our published specifications and to be free from defects in materials and workmanship to the acceptable quality levels defined in these specifications. If acceptable quality levels are not specified, the acceptable quality levels will be those normally supplied by us for the product. We make no guarantee of the results to be obtained from the use of our products. The determination as to the adaptability of any of our products to the specific needs of the Buyer is solely Buyer's prerogative and responsibility. We are glad to offer suggestions on the use of our products. Nevertheless, there are no warranties given except such expresses warranties offered in connection with the sale of a particular product. Our liability shall be limited to replacement of, or refund of an amount not to exceed the purchase price attributed to, the goods as to which such claim is made. Our selection of one of these alternatives shall be Buyer's exclusive remedy. IN NO CASE SHALL WE BE LIABLE FOR CONSEQUENTIAL OR SPECIAL DAMAGES, EVEN IF WE HAVE BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES. THE FOREGOING WARRANTIES ARE IN LIEU OF ALL OTHER WARRANTIES, GUARANTEES, CO-CONDITIONS AND REPRESENTATIONS, EITHER EXPRESSED OR IMPLIED, WHETHER ARISING UNDER ANY STATUTE, COMMON LAW, USAGE OR TRADE, COURSE OF DEALING OR OTHERWISE, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.