

Safe-Cure[®] 3500

MTO Approved, White Pigmented, Concrete Curing Compound

SPECIALTY CONSTRUCTION PRODUCTS

R Т **D A T A** О П

DESCRIPTION

Safe-Cure 3500 is a water based, white pigmented, concrete curing compound. It is formulated specifically to meet the standards established by the Ontario Ministry of Transportation (MTO).

USES

- Curing compound for Province of Ontario paving projects
- Curing compound for projects requiring a higher level of water retention
- Mass concrete, dams, mat foundations

ADVANTAGES

- Meets the industry standard for pigment and solids • suspension, reduces length and frequency of agitation
- Excellent moisture retention
- White pigments reflect heat in hot weather and act as a gauge of proper application rate
- Superior spraying characteristics for economical application and reduced labor cost
- Meets ASTM C309, Type 2, Class A specifications

Packaging Product Number			
5 gal (18.9L)	36 per pallet	F1625.05	
55 gal (208L)	4 per pallet	F1625.55	
275 gal (1040L)		F1625.275	
Bulk tanker up to 5,500 gal (20,790L)		F1625.00	

TECHNICAL DATA

- for concrete curing compounds.
- for Curing Concrete
- Meets AASHTO M-148, Type 2, Class B •
- CSI Master Format 03 39 00

Test Data		
V.O.C.	< 350 g/L	
Solids %	24+/-2	
Water Loss kg/m ²	<0.55 @75 hours	
Flash Point °F (°C)	>200 (93)	
Light Reflectance	65% minimum	
Settling (150 ml Kimax cylinder)	< 5 ml in 2 hrs <25 ml in 24 hrs	

Estimating Guide Coverage dependent on surface texture and porosity	
Curing	200 (5 m²/L)

DIRECTIONS

Application: Apply Safe-Cure 3500 after all bleed water has dissipated and application will not mar surface. Apply

uniformly leaving no pinholes or gaps. Do not allow material to puddle.

Mixing: Do not dilute. Stir or agitate Safe-Cure 3500 before using to disperse pigments and solids uniformly. If using a pump, use an air diaphragm pump to circulate Safe-Cure 3500. Do not use a centrifugal pump. Mix only long enough to make the Safe-Cure 3500 homogenous. Do not over mix as this may cause foaming and may damage the curing compound.

Spray Application: Always use a dedicated sprayer for water-based curing and sealing products. Use a low pressure airless sprayer equipped with a fan nozzle of 0.030 to 0.035" at 1 gallon per minute. The optimum spray pattern Meets all Ontario Ministry of Transportation requirements is a 8 to 12" (20 to 30 cm) fan. Hold sprayer tip 8 to 12" (20 to 30 cm) from the concrete surface.

Meets ASTM C309, Type 2, Class B, Standard Roller Application: Use a short napped roller (3/8" or less). Specification for Liquid Membrane-Forming Compounds Drying Time: Safe-Cure 3500 dries in less than 4 hours at 70°F (21°C) at 50% relative humidity. Cooler temperatures or higher relative humidity may slow drying process.

Clean Up: Clean tools and equipment immediately after use with warm water and detergent.



ChemMasters

January 2019

An American Owned & Operated Company

300 EDWARDS STREET • MADISON, OHIO 44057 - 3112 (440) 428-2105 • FAX (440) 428-7091 • ORDER LINE: (800) 486-7866 www.chemmasters.net

LIMITATIONS

- Safe-Cure 3500 is not recommended for interior use or where appearance is important
- Do not apply if surface or ambient temperature is be-• low 40°F (4°C). Product must be conditioned to 50°F (10°C) prior to application.
- Do not allow product to freeze.
- Do not use Safe-Cure 3500 as a bond breaker for tilt-• up construction.

STORAGE

Store in tightly closed containers out of direct sunlight between 50 and 100°F (10 and 38°C). Storing in direct sunlight or at high temperatures may cause bacterial growth which can destroy the product. Bacterial growth will cause the product to appear gray in color and create an objectionable odor. Product should not be used if this occurs. Shelf life of properly stored material is one year from date of manufacture.

Make certain that the most current version of the Product Data Sheet and Safety Data Sheet are being used. Go to www.chemmasters.net or contact ChemMasters Technical Service at 800-486-7866 to verify the most current version.

Product selection and application are the sole responsibility of the user. ChemMasters can only make technical recommendations and cannot provide jobsite quality control. All label and SDS precautions must be fully understood before use.

PRECAUTIONS:

WARNING: May be harmful if swallowed. Causes eye irritation. May cause an allergic skin reaction.

Precautionary Statements: Avoid breathing dust/fume/ gas/mist/vapors/spray. Wash hands and skin thoroughly after handling. Contaminated work clothing should not be allowed out of the workplace. Wear protective gloves/ protective clothing/eye protection/face protection.

All label precautions and Safety Data Sheet must be fully understood before using this product. Keep out of the reach of children.

This Product is Formulated and Labeled for Industrial and Commercial Use Only

FOR BEST RESULTS AND SAFEST USAGE, USER IS SPECIFICALLY DIRECTED TO CONSULT THE CURRENT PRODUCT & SAFETY DATA SHEETS AND PACKAGE LABEL FOR THIS PRODUCT We warrant our products to meet our published specifications and to be free from defects in materials and workmanship to the acceptable quality levels defined in these specifications. If acceptable quality levels are not specified, the acceptable quality levels will be those normally supplied by us for the product. We make no guarantee of the results to be obtained from the use of our products. The determination as to the adaptability of any of our products to the specific needs of the Buyer is solely Buyer's prerogative and responsibility. We are glad to offer suggestions on the use of our products. Nevertheless, there are no warranties given except such expresses warranties offered in connection with the sale of a particular product. Our liability shall be limited to replacement of, or refund of a mount not to exceed the purchase price attributed to, the goods as to which such claim is made. Our selection of one of these alternatives shall be Buyer's exclusive remedy. IN NO CASE SHALL WE BE LIABLE FOR CONSEQUENTIAL OR SPECIAL DAMAGES, EVEN IF WE HAVE BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES. THE FOREGOING WARRAN-TIES ARE IN LIEU OF ALL OTHER WARRANTIES, GUARANTEES, CO-CONDITIONS AND REPRESENTATIONS, EITHER EXPRESSED OR IMPLIED, WHETHER ARISING UNDER ANY STATUTE, COMMON LAW, USAGE OR TRADE, COURSE OF DEALING OR OTHERWISE, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. @2015ChemMasters