



ChemMasters®

Safe-Cure® & Seal EPX

Water-Based Epoxy Cure & Protect,
Primer & Coating

SPECIALTY CONSTRUCTION PRODUCTS

P R O D U C T D A T A

DESCRIPTION

ChemMasters' **Safe-Cure & Seal EPX** is a low-VOC, two component, water-based epoxy, cure and protect and primer for concrete. It effectively cures fresh concrete and protects concrete surfaces from freeze/thaw cycles, deicing chemicals, dirt and other contaminants. **Safe-Cure & Seal EPX** is also a high performance primer for use with ChemMasters **Duraguard 310CRU** and **GreenThane 310WB** pigmented coating systems. It is available in clear, pigmented, or white primer formulations.

USES

- Use on interior or exterior, horizontal or vertical, concrete surfaces.
- Curing fresh concrete to provide effective hydration of the cement to ASTM C1315 standards.
- High performance coating for formed and poured, tilt wall, or precast structures.
- Curing compound and epoxy primer for **Duraguard 310 CRU** and **GreenThane 310WB** in D.O.T. concrete coating applications including bridge, median, and sound barrier surfaces.

ADVANTAGES

- Cures, protects, and primes in a single economical application.
- May be top coated with pigmented **Safe-Cure & Seal EPX**, **Duraguard 310 CRU** or **GreenThane 310WB**
- Eliminates costly chemical or mechanical removal of curing membrane prior to application of polymer coatings.
- Excellent resistance to chloride ion penetration yet exhibits high level of moisture vapor transmission when fully cured.
- Significantly improved wear and chemical resistance over standard resin or acrylic curing compounds.
- Exceptional tensile and shear bond strengths for improved durability.

TECHNICAL DATA

APPLICABLE STANDARDS

- ASTM C-309, Type I* Class A & B Standard Specification for Liquid Membrane Forming Compounds for Curing Concrete
- ASTM C-1315 Type I*, Class B, Standard Specification for Liquid Membrane-Forming Compounds for Curing and Sealing Concrete
- AASHTO M-148, Type 1* Class A & B
- Complies with National Volatile Organic Compound (VOC) Emission Standards for Architectural Coatings, Federal EPA Regulation 40 CFR Part 59
- Ohio D.O.T. Material Specification 705.23A Item 512.03.
- Available in clear or any Federal Standard color
- Type II when pigmented white

Physical Properties

Solids: Colors Clear	38 to 45% 31%
Weight	9 lbs/gal (1.07 kg/L)
VOC content	< 50 g/L
Flash Point	>200°F
Pot Life	30 minutes
ASTM C 1315 Moisture Loss	<0.40 g/cm ² in 72 hrs
Abrasion Resistance Taber 1kg//500 cycles/CS 10 wheels Taber 1kg//1000 cycles/CS 10 wheels	18.1 mg 33.1 mg
Tensile Bond Strength (7 days): Fresh concrete Etched or blasted concrete	215 to 220 psi (1.4 to 1.5 MPa) 350 to 450 psi (2.4 to 3.1 MPa)
ASTM C882 Shear Bond Strength (7 days)	1000 psi (21.4 MPa)

Packaging of 4 gallon unit / Part Number

Clear Part A & B	0.8 gal in 1 gal pail (A) 3.2 gal in 5 gal pail (B)	F5000.050W
White Primer Part A & B	0.8 gal in 1 gal pail (A) 3.2 gal in 5 gal pail (B)	F5005.05



ChemMasters®

An American Owned & Operated Company

300 EDWARDS STREET • MADISON, OHIO 44057-3112 (440)428-2105 • FAX (440)428-7091 • ORDER LINE: (800)486-7866 www.chemmasters.net

June 2023

Drying Time @ 70°F (21°C) with 50% R.H.

Dry to _ condition:	Hours
Dry	4 (longer when humidity is high)

Estimating Guide *

(Coverage Rates Vary with Surface Texture and Porosity.
For DOT jobs check specific requirements)

Condition	ft ² /gallon	m ² /liter
Curing & Sealing Fresh Concrete	200	5
Priming & Coating Cured Concrete	200	5

DIRECTIONS

Mixing: **Safe-Cure & Seal EPX** must be mixed before application. **Add entire contents of Part A into the 5 gal pail of Part B.** Mix for 3 minutes with a drill at low speed fitted with a mixing blade to minimize the risk of incorporating excess air. (Pigmented formulations must have a uniform color with no streaks). Stop mixing, allow epoxy to rest for 5 minutes. A noticeable fattening or thickening of the material will be evident. Remix for one minute just prior to use. Use within 30 minutes.

Application: A medium nap roller is preferred for surfaces exhibiting an enlarged pore structure, numerous bug holes, honey combs, or voids. Apply evenly leaving no pinholes or gaps but avoid puddles.

Safe-Cure & Seal EPX may also be sprayed using a Chapin Sprayer with a 0.30 to 0.40" fan tip, GRACO Gmax 5900 HD 1 gpm Blue HD Texture Gun using a fan tip with minimum tip size 0.017 GHD, and 2,000 psi, or comparable. Hold sprayer tip 6 to 8 in (15 to 20 cm) from the concrete surface. Apply uniformly leaving no pinholes or gaps. Avoid over applying or forming puddles.

When applying **Safe-Cure & Seal EPX** on horizontal surfaces apply after all bleed water has dissipated and application will not mar surface. When curing slip formed concrete, apply immediately following slip form machine.

When sealing or priming steel trowel or previously cured concrete, the surface must be cleaned, acid etched, and thoroughly rinsed prior to applying **Safe-Cure & Seal EPX**. Exterior concrete must be brushed blasted or high pressure washed before application. The surface may be damp when the epoxy is applied but there should be no puddles.

Drying and Re-coating: **Safe-Cure & Seal EPX** dries to the touch in 4 hours @ 70°F (21°C) and 50% relative humidity. Lower temperatures and higher humidity will take longer to dry. Environmental conditions affect curing and drying time. The surface may be recoated when it is tack free. Recoating must be completed within 7 days. After 7 days additional surface preparation will be required. Contact ChemMasters' Technical Service Department for details.

Low temperature and high humidity slow the drying process. **Safe-Cure & Seal EPX** must be tack free before applying a second coat. Ensure there are no contaminants that could interfere with the adhesion on the surface.

CLEANUP

Clean tools and equipment used to apply **Safe-Cure & Seal EPX** with warm water and detergent immediately after use.

LIMITATIONS

- **Safe-Cure & Seal EPX** must be applied within 1.5 hrs of finishing operation when used as a curing compound
- State D.O.T. specifications pertaining to coverage rates supersede those recommended by ChemMasters. Consult project specifications or proposal notes for state requirements
- **Safe-Cure & Seal EPX** is not to be used as a bond breaker for tilt wall construction.
- For optimum results, condition material to 60 to 75°F (15 to 24°C) prior to mixing. This is critical when temperature is above 90°F (32°C).
- **Safe-Cure & Seal EPX** is not intended for use when concrete surface temperatures are below 50°F (10°C)
- Increasing mixed mass (volume) decreases working time (pot life)

STORAGE

Store tightly closed containers between 50 and 100°F (10 and 38°C) in unopened containers out of direct sunlight and precipitation. **Do not freeze!** Shelf life of properly stored material is two years from date of manufacture.

PRECAUTIONS:

Part A: WARNING: Harmful if swallowed. Causes skin irritation. May cause an allergic skin reaction. Causes serious eye irritation. May cause respiratory irritation. Toxic to aquatic life with long lasting effects. Precautionary Statements: Avoid breathing dust/fume/gas/mist/vapors/spray. Wash hands and skin thoroughly after handling. Do not eat, drink or smoke when using this product. Use only outdoors or in a well ventilated area Contaminated work clothing should not be allowed out of the workplace. Avoid release to the environment. Wear protective gloves/protective clothing/eye protection/face protection.

Part B: WARNING: Causes skin irritation. May cause an allergic skin reaction. Causes serious eye irritation. May cause respiratory irritation. Precautionary Statements: Avoid breathing fume/gas/mist/vapors/spray. Wash hands and skin thoroughly after handling. Use only outdoors or in a well-ventilated area. Contaminated work clothing should not be allowed out of the workplace. Wear protective gloves/protective clothing/eye protection/face protection. In case of inadequate ventilation wear respiratory protection.

Consult the Safety data sheet for full hazard information.

This Product is Formulated and Labeled for Industrial and Commercial Use Only

FOR BEST RESULTS AND SAFEST USAGE, USER IS SPECIFICALLY DIRECTED TO CONSULT THE CURRENT PRODUCT & SAFETY DATA SHEETS AND PACKAGE LABEL FOR THIS PRODUCT. We warrant our products to meet our published specifications and to be free from defects in materials and workmanship to the acceptable quality levels defined in these specifications. If acceptable quality levels are not specified, the acceptable quality levels will be those normally supplied by us for the product. We make no guarantee of the results to be obtained from the use of our products. The determination as to the adaptability of any of our products to the specific needs of the Buyer is solely Buyer's prerogative and responsibility. We are glad to offer suggestions on the use of our products. Nevertheless, there are no warranties given except such expresses warranties offered in connection with the sale of a particular product. Our liability shall be limited to replacement of, or refund of an amount not to exceed the purchase price attributed to, the goods as to which such claim is made. Our selection of one of these alternatives shall be Buyer's exclusive remedy. IN NO CASE SHALL WE BE LIABLE FOR CONSEQUENTIAL OR SPECIAL DAMAGES, EVEN IF WE HAVE BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES. THE FOREGOING WARRANTIES ARE IN LIEU OF ALL OTHER WARRANTIES, GUARANTEES, CO-CONDITIONS AND REPRESENTATIONS, EITHER EXPRESSED OR IMPLIED, WHETHER ARISING UNDER ANY STATUTE, COMMON LAW, USAGE OR TRADE, COURSE OF DEALING OR OTHERWISE, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.